

各種二相系ステンレス鋼の規格、成分

UNS No	JIS,AISI No, Common Name	C	Si	Mn	P	S	Cr	Mo	Ni	その他
	SUS329J1	0.08	1	1.5	0.04	0.03	23.0/28.0	1.0/3.0	3.0/6.0	
	SUS329J3L	0.03	1	2	0.04	0.03	21.0/24.0	2.5/3.5	4.5/6.5	N 0.08/0.20
	SUS329J4L	0.03	1	1.5	0.04	0.03	24.0/26.0	2.5/3.5	5.5/7.5	N 0.08/0.30
S31100	XM-26	0.06	1	1	0.045	0.03	25.0/27.0	-	6.0/7.0	Ti 0.25
S31200	44LN	0.03	1	2	0.045	0.03	24.0/26.0	1.20/2.00	5.5/6.5	N 0.14/0.20
S31260	DP3	0.03	0.75	1	0.03	0.03	24.0/26.0	2.5/3.5	5.5/7.5	N 0.10/0.30; Cu 0.20/0.80; W 0.10/0.50
S31500	3RE60	0.03	1.4/2.0	1.2/2.0	0.03	0.03	18.0/19.0	2.5/3.0	4.25/5.25	N 0.05/0.10
S31803	2205	0.03	1	2	0.03	0.02	21.0/23.0	2.5/3.5	4.5/6.5	N 0.08/0.20
S32001	-	0.03	1	4.0/6.0	0.04	0.03	19.5/21.5	0.6	1.00/3.00	N 0.05/0.17; Cu 1.00
S32003	-	0.03	1	2	0.03	0.02	19.5/22.5	1.50/2.00	3.0/4.0	N 0.14/0.20
S32101	LDX 2101	0.04	1	4.0/6.0	0.04	0.03	21.0/22.0	0.10/0.80	1.35/1.70	N 0.20/0.25; Cu 0.10/0.80
S32205	2205 UR45N	0.03	1	2	0.03	0.02	22.0/23.0	3.0/3.5	4.5/6.5	N 0.14/0.20
S32304	2304 UR35N	0.03	1	2.5	0.04	0.03	21.5/24.5	0.05/0.60	3.0/5.5	N 0.05/0.20; Cu 0.05/0.60
S32404	Uranus 50	0.04	1	2	0.03	0.01	20.5/22.5	2.0/3.0	5.5/8.5	N 0.20; Cu 1.0/2.0
S32520	Uranus 52N+	0.03	0.8	1.5	0.035	0.02	24.0/26.0	3.0/4.0	5.5/8.0	N 0.20/0.35; Cu 0.50/2.00
S32550	Ferralium 255	0.04	1	1.5	0.04	0.03	24.0/27.0	2.9/3.9	4.5/6.5	N 0.10/0.25; Cu 1.50/2.50
S32750	2507	0.03	0.8	1.2	0.035	0.02	24.0/26.0	3.0/5.0	6.0/8.0	N 0.24/0.32; Cu 0.50
S32760	Zeron 100	0.03	1	1	0.03	0.01	24.0/26.0	3.0/4.0	6.0/8.0	N 0.20/0.30; Cu 0.5/1.00; W 0.50/1.00
S32900	329 44L 453S	0.08	0.75	1	0.04	0.03	23.0/28.0	1.00/2.00	2.0/5.00	-
S32906	-	0.03	0.5	0.80/1.50	0.03	0.03	28.0/30.0	1.50/2.60	5.8/7.5	N 0.30/0.40; Cu 0.80
S32950	7Mo Plus	0.03	0.6	2	0.035	0.01	26.0/29.0	1.00/2.50	3.5/5.2	N 0.15/0.35
S39226	-	0.03	0.75	1	0.03	0.03	24.0/26.0	2.50/3.50	5.50/7.50	N 0.10/0.30; Cu 0.20/0.80; W 0.10/0.50
S39274	DP3W	0.03	0.8	1	0.03	0.02	24.0/26.0	2.50/3.50	6.0/8.0	N 0.24/0.32; Cu 0.20/0.80; W 1.50/2.50
S39277	AF918	0.025	0.025	-	0.025	0.002	24.0/26.0	3.0/4.0	6.5/8.0	N 0.23/0.33; Cu 1.2/2.0; W 0.80/1.20